

**PCT**

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> C05C 9/00, C05G 5/00 B01J 8/24, B05D 7/00	<b>A1</b>	<b>(11) International Publication Number:</b> WO 91/14663 <b>(43) International Publication Date:</b> 3 October 1991 (03.10.91)
<b>(21) International Application Number:</b> PCT/US91/01950 <b>(22) International Filing Date:</b> 22 March 1991 (22.03.91)  <b>(30) Priority data:</b> 497,442                      22 March 1990 (22.03.90)                      US  <b>(71) Applicant:</b> THE O.M. SCOTT & SONS COMPANY [US/ US]; 14111 Scottslawn Road, Marysville, OH 43041 (US).  <b>(72) Inventors:</b> THOMPSON, Harold, Edward ; 1914 Slaton Court, Columbus, OH 43235 (US). KELCH, Richard, Alan ; 6901 Meadow Oak Drive, Columbus, OH 43235 (US).		<b>(74) Agents:</b> RADEN, James, B. et al.; Jones, Day, Reavis & Pogue, 225 West Washington Street, Chicago, IL 60606 (US).  <b>(81) Designated States:</b> AT (European patent), AU, BE (Euro- pean patent), CA, CH (European patent), DE (Euro- pean patent), DK (European patent), ES (European pa- tent), FI, FR (European patent), GB (European patent), GR (European patent), HU, IT (European patent), JP, KR, LU (European patent), NL (European patent), NO, SE (European patent).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> ENCAPSULATED SLOW RELEASE FERTILIZERS  <b>(57) Abstract</b>  A coated product comprising a water soluble core material having a water insoluble polymeric coating encapsulating said core and a process for the production thereof. The encapsulating coating comprising a water-borne, polyvinylidene chloride-based latex composition which provides for the release of the water soluble core material over an extended period of time.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark				

-1-

DESCRIPTIONENCAPSULATED SLOW RELEASE FERTILIZERS

5

TECHNICAL FIELD

10 The present invention relates to controlled-release products of the slow release type and to processes for the production thereof and, in particular, to encapsulated or coated granular or particulate products which release their nutrient content at a slow, controlled rate over time.

15 Encapsulated fertilizers are known to be very effective and efficient sources of slow release nutrients for the long-term feeding of plants. The nutrients are released at slow, controlled rates through the fertilizer's coating resulting in a sustained feeding of  
20 the plants. As a result, one application of an encapsulated fertilizer can provide the necessary nutrients for a plant that would ordinarily take multiple applications of soluble fertilizers. In addition, encapsulated fertilizers can also be more efficient and  
25 cause less environmental concerns than soluble fertilizers due to their slow release of nutrients. Since the nutrients are released at a slow sustained rate rather than a sudden surge, more of the nutrients are absorbed by the plant and thus are not washed away or leached through  
30 the soil, where they can enter the ground water.

One type of slow release encapsulated fertilizer currently in wide use for both nursery and turf applications is sulfur coated fertilizer. Coating weights ranging from 15 to 35% by weight are applied to granular fertilizer in coating drums. There are two modes of

-2-

release of the sulfur coated fertilizer's nutrients. The first is by diffusion through cracks and other imperfections in the sulfur coating. This allows the nutrients to be released rather quickly, and is the predominate mode of release for short-term fertilizer products. The second mode of nutrient release is through coating breakdown. This allows for the longer residual feeding of plants and thus is the primary mode of release for nursery-type sulfur coated fertilizers. The major advantage of the sulfur coated fertilizers is their relatively low cost. This is due to low raw material costs as well as inexpensive manufacturing costs associated with the coating drum process.

A second type of encapsulated slow release fertilizer utilizes solvent applied polymer coatings. For this type of encapsulated fertilizer, the polymer is first dissolved in an organic solvent and then sprayed onto the fertilizer base in either a coating drum or a fluid bed. As the solvent evaporates, a very uniform, continuous polymer film is left behind, forming the fertilizer's barrier coating. Examples of solvent applied polymer coated fertilizers which are currently in use in the nursery industry are disclosed in U.S. Patent No. 4,019,890, issued to Fugita et al., April 26, 1977 and U.S. Patent No. 3,223,518 to Hansen on December 14, 1965.

Another type of encapsulated fertilizer that exhibits good slow release properties is latex coated granular fertilizers such as those disclosed in U.S. Patent No. 4,549,897 issued to Seng et al., on October 29, 1985 and Korean Patent No. 88-153 issued to Mun et al., on March 12, 1988. Such latex coated fertilizers are produced by first applying a sodium silicate precoat to the fertilizer core to protect it from dissolution caused by the water-borne latex. After precoating has been completed, a

-3-

high molecular weight polymer latex top coat is applied to the precoated fertilizer core. As the water from the latex evaporates, a continuous film, similar to that left behind during solvent-applied polymer coating, is left  
5 surrounding the fertilizer granule. It is this latex top coat which gives the encapsulated fertilizer most of its sustained release properties.

Solvent and latex applied polymer encapsulated fertilizers both offer similar important benefits over  
10 sulfur coated products concerning consistency of release rates and the ability to provide extended fertilizer residuals. These benefits are chiefly due to the uniform, continuous, and rather defect-free film coating which surrounds the fertilizer core in each product type. These  
15 polymer coatings are also very tough and durable and generally are not prone to significant mechanical breakdown. In addition, the coatings are biologically inert and, thus, are not susceptible to breakdown resulting from microbial activity in the soil or other  
20 potting media. As a result, the majority of the nutrient release is by diffusion through the polymer coat, rather than release through imperfections and flaws or as a result of particle breakdown. This allows for a much more uniform and consistent nutrient release rate and, if the  
25 barrier properties of the polymer are sufficient, a longer residual nursery-type encapsulated fertilizer than sulfur coated products.

However, sulfur coated fertilizers offer certain advantages over soluble fertilizers such as providing  
30 somewhat slower release of nutrients, and being less costly than other encapsulated fertilizers. Conversely, there are some disadvantages to the sulfur coated fertilizers, which, as a result of imperfections and coating degradation, tend to be highly variable and lead

-4-

to inconsistencies in the product's release rate. As the number of coating imperfections increases, so does the fertilizer's nutrient release rate. In addition, the sulfur coating is fairly brittle. With increased  
5 handling, the coating breaks down causing further variability and increase in the nutrient release rate.

Another inherent disadvantage of sulfur coated fertilizers is the problem with soil acidulation. As the sulfur coating begins to break down, the free sulfur  
10 combines with water to form an acid. This does not create a problem with turf applications where there is plenty of soil available to dilute the effect of the acid, but can be a problem with potted plants where the acid can significantly lower the potting media's pH, which can  
15 cause damage to the plants and retard their growth.

Solvent applied polymer encapsulated fertilizers, such as those disclosed in U.S. Patent Nos. 4,019,890 and 3,223,518 also have problems associated therewith. For example, they require the use of organic solvents to  
20 dissolve the polymers before they can be applied to the fertilizer core. This presents an economic disadvantage for the solvent-based polymer encapsulation processes in addition to presenting potential health and environmental hazards.

25 Organic solvents, such as those used for polymer dissolution, tend to be very expensive. To help offset this high cost, a solvent recovery system must be used in conjunction with the coating process to aid in the reduction of fresh solvent requirements. Although such a  
30 solvent recovery system does reduce the amount of fresh solvent required, thus lessening solvent costs, it increases the overall manufacturing conversion cost of the polymer coating process. As a result, the production costs for solvent applied polymer encapsulated fertilizers

-5-

are higher than processes which do not use solvents thus presenting a problem of economics relative to such processes and their resulting products. In addition, the capital costs for a solvent recovery system are quite high  
5 which causes a further economic problem in regard to the commercial application of such encapsulation techniques.

Another problem presented by the implementation of solvent-based polymer encapsulation processes concerns health issues presented by the toxic nature of many  
10 organic solvents used therein. These solvents and the vapors they emit can be very harmful to humans. Most organic solvents also are very volatile, posing both fire and explosion hazards. Further, uncontained solvent spills outside the production facility and emissions of  
15 vapors into the atmosphere present potential environmental problems. As a result of these potential health and environmental issues, extra caution, as well as increased capital, must be allocated for such processes using organic solvents.

20 Prior latex encapsulated fertilizers as exemplified by those disclosed in Korean Patent No. 88-153 also have major problems associated therewith. The processing conditions taught therein combined with the physical properties of the water-borne latex top coat employed, do  
25 not enable water removal quickly enough to prevent dissolution of the soluble fertilizer core. Therefore, a hydrophobic precoat, such as sodium silicate, must first be applied to the fertilizer core protecting it from dissolution. Once the precoat has been applied, the latex  
30 top coat can be applied, but this two-stage coating operation causes a problem of economic feasibility by increasing both the raw material and operating costs which results in a significant increase in product cost.

-6-

## SUMMARY OF THE INVENTION

It is a primary object of the present invention to provide controlled release products which combine low cost and minimal health and environmental risks with excellent  
5 slow rates of release.

It is a more specific object of this invention to provide encapsulated or coated granular or particulate products, especially fertilizer products, which are particularly effective for providing uniform and  
10 consistent controlled release of nutrients sustained over a long residual period of time.

A further object of this invention is to provide a relatively simple and economical process for the preparation of controlled release encapsulated or coated  
15 granular or particulate products such as fertilizer products.

The foregoing and other objects of the invention are achieved by providing latex encapsulated granular products which include water-borne, polyvinylidene chloride-based  
20 latexes as encapsulants or coatings for particulate water-soluble core materials such as fertilizer granules. In regard to encapsulated granular fertilizer products produced in accordance with the present invention, it has been found that such products exhibit nursery-type  
25 controlled release properties. Also, it is to be noted that such products are produced without the use of hydrophobic precoat which were previously considered to be essential to protect the water-soluble core material from dissolution resulting from the application of  
30 water-based latexes thereon.

The products of the present invention are prepared by coating a water-soluble granular core material such as a fertilizer material with a water-borne polyvinylidene chloride-based latex material. The latex material may be



-7-

applied to the core by spray coating in a fluidized bed with hot air drying. In order to accommodate such processing, it has been found that the latex coating materials employed herein must possess certain characteristics in order to enable production of suitable coated or encapsulated products. For example, latexes suitable for use herein have been found to have low viscosity characteristics in order to enable low pressure spraying thereby reducing or eliminating shear related breakdown of the coating. Also, the latexes useful herein have been found to have a high solids content in order to avoid the need to utilize harsh drying conditions in the process. Furthermore, latexes suitable for use herein have been found to exhibit glass transition temperatures and blocking temperatures which result in the production of coated or encapsulated products without encountering agglomeration and blocking problems in the production thereof.

20

## DETAILED DESCRIPTION

While the present invention is useful for the controlled release of a variety of active constituents it is primarily useful for the controlled release of fertilizers and accordingly, will be specifically described in connection with a water soluble fertilizer substrate. However, it is to be recognized that the invention is also applicable to the coating of other water soluble active constituents where prolonged or controlled release is desirable, including pesticides, herbicides, fungicides, growth regulators, insecticides and animal and insect repellents. Such active constituents are well known and examples are set forth in the literature. It is preferable that the active constituent be in solid, granular or particulate form and it should not decompose

25

30

-8-

or melt at processing temperatures. In addition, the active constituent will normally be moderately to highly water soluble. Thus, a principle object in the use of the coated or encapsulated products of the present invention is to control the leaching of the active constituent therefrom with water.

The latex coating may be applied to the fertilizer by a number of methods. However, in a most preferred embodiment of this invention the latex is coated on the fertilizer granules by spray coating in a fluidized bed such as a Wurster column or similar device until the latex is distributed over the particles. Preferably, the spray coating is performed at an application rate of about .0025 grams latex per gram of fertilizer granule per minute to about .0083 grams latex per gram of fertilizer granule per minute utilizing a fluidizing air flow rate in the range of about 1-6 cubic meters per hour per gram of water to be removed from the coating and at a temperature in the range of about 35-60°C.

After the coating of the latex over the particles is completed, the resulting coated product is, preferably, air dried. In accordance with this preferred method of the present invention, it has been found that latex coating weights of from about 4% to about 20% by weight and, more preferably, about 6-15% are effectively achieved.

Suitable latexes for use in the present invention as encapsulating coatings for the granular or particulate fertilizers have been found to include copolymer blends of predominately vinylidene chloride monomers and ethylenically unsaturated comonomers selected from the group consisting of methyl methacrylates, acrylonitriles and methyl acrylates. Other latexes suitable for use herein are vinylidene chloride-vinyl chloride copolymers and mixtures thereof.

-9-

Exemplary of particularly preferred water-borne, polyvinylidene chloride-based latex compositions for use herein are the emulsion polymerized vinylidene chloride copolymer latexes disclosed in U.S. Patent 4,401,788; the disclosure of which is incorporated herein by reference. A latex of similar composition is sold under the trademark Daran SL112 by W.R. Grace & Co. and has the following properties: Total Solids - 54%; pH-2; Particle Size - 0.11 microns; viscosity (Brookfield RVT, No. 1 Spindle at 30 rpm) - < 30 cps; Weight per Gallon - 10.6 lbs.; Surface Tension - 60-68 dynes/cm.; and Freezing Point - 36°F.

Another particularly advantageous vinylidene chloride based copolymer latex for use herein is sold by Solvay & Cie under the trademark IXAN WA 50, an aqueous anionic dispersion of a copolymer with a high content of vinylidene chloride, in the form of a milky white liquid of low viscosity having the following properties: Dry Solids Content - 55 I 2%; Density - approximately 1.282 kg/dm<sup>3</sup>; Surface Tension - 29-34 dynes/cm.; pH - 2-3.5; Dynamic Viscosity at 20°C - approximately 14 cP and Minimum Film-Forming Temperature - 17-19°C.

A further preferred latex for use herein as a coating for granular particles is sold by BF Goodrich Company under the trademark Geon 650X18, a uniform colloidal dispersion of vinyl chloride polymers and vinylidene chloride copolymers in water. Geon latexes are true colloids, having spherical particles, usually of 0.2 micron average diameter or smaller and are produced by emulsion polymerization.

Each of the foregoing latexes exhibits the necessary film forming properties and contains low concentrations of both anionic and nonionic surfactants. They also, have high solids contents (e.g., greater than 50% by weight solids) and demonstrate low, water-like viscosities (e.g.

-10-

less than 30 cps), glass transition temperatures in the range of about 15°C to about 35°C and blocking temperatures of at least about 32°C. The latexes employable herein further demonstrate very good moisture barrier properties to enable slow, controlled release of the fertilizer core nutrients.

Preferably, the vinylidene chloride based copolymer latexes useful in the present invention include from about 80 to about 92% by weight vinylidene chloride and from about 5 to about 14% by weight ethylenically unsaturated comonomers. With regard to these comonomers, on a percentage by weight basis, the methyl methacrylates are preferably present, in an amount of about 2.5- 4%; the acrylonitriles, in an amount of about 1-8% and the methyl acrylates, in an amount of about 1-2%. The comonomers help to reduce the crystallinity of vinylidene chloride and, also, improve the physical properties of the latexes. These latexes also contain between 0.05 and 0.5% by weight of an anionic surfactant from the group consisting of sodium alkylbenzenesulfonates, sodium salts of alkyl sulfonic acid esters, sodium salts of sulfosuccinic acid alkyl esters, sodium alkylsulfonates, sodium alkylidiphenylether sulfonates, sulfuric acid esters of alkylphenolpolyethylene oxides and mixtures thereof and from 3 to 5% by weight of a nonionic surfactant from the group consisting of alkylethers, alkylphenol ethers, fatty acid esters of polyethylene oxides and mixtures thereof. The surfactants add stability to latexes by keeping the polymers from agglomerating and improve resistance to shear which could cause the latexes to prematurely breakdown.

A critical property of these latexes, as applied to spray coating, is viscosity. A low viscosity allows for easy conveyance of the latex through tubes and piping at

-11-

ambient temperatures. It also enables the latex to be sprayed onto the fertilizers at low pressures reducing the amount of shear encountered by latexes thus preventing shear related breakdown. The latexes used to coat the fertilizers of this invention have maximum viscosities of 30 centipoise. This is a sufficiently low viscosity to permit the latexes to be easily transported with little pressure requirements and sprayed with a minimum amount of shear.

High polymer solids content of the latexes is also a critical property for successful spray coating operations. When water is not removed quickly enough from the latexes as they are being applied, the partially coated granules become tacky causing reduced fluid bed movement and increased chances for bed agglomeration. Latexes with higher solids contents require less water removal, for an equal coating rate, than do low solids concentration latexes. In order to use latexes with low solids concentrations for coating processes, the fluidization/drying air must be heated to high temperatures to effectively remove the excess water. This additional heat causes further agglomeration concerns, as well as increasing the energy requirements for the coating process. By choosing a latex with a high solids content, such as the latexes used for this invention which have solids contents greater than 50% by weight, the water can easily be removed during coating without using harsh drying conditions.

The glass transition temperature ( $T_g$ ) of a polymer, or copolymer blend, is the temperature below which there is virtually no molecular movement which causes the polymer to become rigid or crystalline-like. As the temperature of the polymer rises above the  $T_g$ , molecular movement begins and as the temperature continues to rise,

-12-

increased molecular movement occurs, resulting in a more pliable polymer. This is important to the successful polymer encapsulation of fertilizers since polymer films, such as those formed around the fertilizer granules during the coating process, become softer and show increased tendencies towards tackiness as the degree of plasticity increases. At coating temperatures 20 to 30°C above the glass transition temperature of latexes, the partially coated fertilizer granules become tacky and cause reduced particle movement in the fluidized bed. After several minutes of reduced bed movement, the fertilizer granules become agglomerated. Separation of the agglomerated particles can cause damage to the coating which destroys the controlled release properties of the encapsulated fertilizer. For this reason, the latexes employed herein for spray coating must have glass transition temperatures no lower than 20-30°C below the desired operating conditions of the coating process.

However, latexes with high glass transition temperatures, those with  $T_g$ 's at or above the operating temperatures of the coating process, have also been found to present problems in use as encapsulants for the granular fertilizer cores herein. In this regard, it has been found that if the coating temperature is not somewhat above the  $T_g$ , of the latex, the latex will not coalesce properly, resulting in a film coating that is neither uniform nor continuous. Thus, it has been determined that the latexes used to prepare the polymer encapsulated fertilizers of this invention should have glass transition temperatures ranging from about 15 to about 35°C. Glass transition temperatures in this range are high enough to enable coating at temperatures between about 35° and about 60°C, the preferred coating and drying range of this invention, without causing agglomeration problems, yet low

-13-

enough to allow for proper coalescence of the latex film, resulting in high quality coatings.

Another property of latexes that is important for fluid bed encapsulation of fertilizers is the minimum blocking temperature. The blocking temperature of a polymer film relates to the temperature above which a film will show signs of blocking, or sticking, when subjected to a force over a period time. As was the case with the glass transition temperature, a polymer will begin to show signs of tackiness as the minimum blocking temperature is exceeded. As the temperature continues to rise above the minimum blocking temperature, the film becomes more tacky, and less force is required to cause agglomeration between particles. Thus, the higher the blocking temperature of the latex, the less likely there will be any signs of blocking during coating. The minimum blocking temperature for the latexes used to prepare the encapsulated fertilizers of this invention have been found to be preferably about 32°C which is sufficiently high to avoid potential blocking problems at the desired coating temperature range.

The mechanism of nutrient release from an encapsulated fertilizer having a uniform, continuous, defect-free coating, such as polymer coated fertilizers, is based on diffusion through the polymer membrane. More specifically, the nutrient release is in a multi-stage process. First, water permeates from outside of the fertilizer granule, through the polymer membrane, and to the fertilizer core. Next, the water acts as a solvent to dissolve a portion of the soluble fertilizer core. Finally, the fertilizer and water solution must permeate back through the polymer coating, to the outside of the encapsulated granule, where the nutrients become available for plant usage. Since the fertilizer cores are generally

-14-

very water soluble, the rate determining steps for this process are the permeation through the membrane to the core and back out through the membrane.

Thus, one of the most important film properties determining how effective the controlled, slow release properties of a fertilizer will be, is the moisture barrier abilities of the polymer. A polymer coating possessing good moisture barrier properties, can greatly reduce the rate of nutrient discharge, while providing more consistent release. This results in an effective controlled release fertilizer with greater extended residual as compared with similar encapsulated fertilizers utilizing polymers with moderate barrier properties.

The novel fertilizers of the present invention employ vinylidene chloride based latexes for their barrier coating. Since vinylidene chloride films possess excellent barrier properties, and the latexes used for the encapsulated fertilizers of this invention preferably have such high VdC concentrations (80 to 92% by weight), the barrier properties of these latexes are exceptional. The maximum moisture vapor transmission rate (MVTR) for an 0.1 mil film of these latexes is 2.0 grams per 100 square inches per 24 hours at 100°F and 90% relative humidity. This MVTR is very low which indicates that the latexes used will provide coatings with excellent controlled, slow release properties resulting in very effective encapsulated fertilizers.

Accordingly, it is a significant feature of the present invention to provide encapsulated granular fertilizers which use particular latex compositions to form complete and continuous polymer film coatings around the fertilizer granules. The coatings are very tough and durable and are not subject to coating attrition or breakdown under normal processing and handling



-15-

conditions. The coatings are also very uniform in thickness and essentially defect-free. As a result, virtually all of the nutrient release is by diffusion through a film membrane instead of by diffusion through coating imperfections or release caused by particle breakdown. Since the barrier properties of the latexes are very good, the barrier properties of the encapsulated products are also very good. Thus, the encapsulated fertilizers of the present invention have very consistent and controllable nutrient release rates rather than the constantly varying release patterns associated with other coated fertilizer products such as sulfur coated fertilizers.

It is another feature of the present invention that the polymer encapsulated fertilizers use water-borne latexes to apply polymer coating rather than a solvent-based polymer system. Accordingly, the problems associated with using organic solvents are avoided. The raw material costs of water-borne latexes are less than the combined cost of the solvents and polymers required for solvent-based coating processes. Furthermore, solvent applied polymer coating facilities incorporate solvent recovery systems to decrease raw material costs, but such systems add significantly to operating expenses. Latex based facilities do not require solvent recovery, thus they avoid this added expense and maintain production costs of latex encapsulated fertilizers at a relatively low level when compared to costs of solvent-based encapsulated fertilizers.

A further feature of the present invention utilizing a latex-based encapsulated fertilizer facility as opposed to a solvent system is the elimination of environmental and health concerns associated with the use of organic solvents. The latexes give off no harmful toxic vapors

-16-

and are relatively safe to handle. There is also no danger of either fire or explosion hazards with the latexes since they are water-based. Additionally, the latexes do not give off any environmentally harmful vapors.

5 It is another significant feature of the present invention that the latex encapsulated fertilizers are produced by applying the latex coatings directly to the water soluble fertilizer cores without using hydrophobic precoats. More particularly, it has been found that the  
10 physical properties of the latexes utilized herein to produce the coatings preferably having high solids contents of 50% or more, glass transition temperatures between 15°C and 35°C, and minimum blocking temperatures greater than 32°C enable the removal of the water content  
15 from the latex quickly enough, during coating, so that the fertilizer cores do not dissolve. In view of the elimination of the heretofore standard precoat, the first coating stage is likewise eliminated which results in a lower manufacturing cost for the present latex  
20 encapsulated fertilizers relative to previous precoated present fertilizers.

The following examples illustrate the practice of the invention. All parts are by weight unless otherwise indicated.

25

## EXAMPLE 1

Granular urea, 400 grams, was added into a bench-scale fluidized bed Wurster column. A vinylidene chloride-based latex (Daran SL112), 130.7 grams, 70.6 grams on a dry  
30 solids basis, was applied to the fluidized urea by spraying from the bottom of the bed at a rate of 1.82 g./min. (0.00455 gram latex/gram fertilizer granule/minute). The fluidization/drying air flow rate was maintained between 118-120 m<sup>3</sup>/hr. (2.35-2.39

-17-

m<sup>3</sup>/gram of water removed) and entered the bed at a temperature of 47°C. The air exited the bed between 40 and 41°C. The total coating time was 72 minutes which was followed by an additional 15 minutes of drying at an air inlet temperature of 47°C and an 18 minute cooling phase using ambient air resulting in a product having a 15% by weight vinylidene chloride-based latex coating on the granular urea.

10

## EXAMPLE 2

A 5% by weight vinylidene chloride-based latex coated granular urea product was prepared in accordance with the procedures of Example 1 except that 380 grams of granular urea and 37.1 grams of Daran SL112 were used to make up the product; the latex was applied to the urea at a coating rate of 1.24 g./min. (0.00326 g. latex/g. fertilizer granule/min.); the fluidization/drying air flow rate ranged from 118 and 125 m<sup>3</sup>/hr. (3.45-3.65 m<sup>3</sup>/g. water removed) and the inlet temperature was maintained at 44°C. The total coating time was 30 minutes followed by 16 minutes of additional drying at temperatures of from 44-56°C and 14 minutes of cooling at ambient temperature.

25

## EXAMPLE 3

An 8% by weight vinylidene chloride-based latex coated granular urea product was prepared in accordance with the procedures of Example 1 except that 380.0 grams of granular urea and 61.2 grams of Daran SL112 were used to make up the product; the latex was applied to the urea at a coating rate of 2.04 g./min. (0.00537 g. latex/g. fertilizer granule/min.). The fluidization/drying air flow rate ranged from 130 to 140 m<sup>3</sup>/hr. (2.31-2.49 m<sup>3</sup>/g. water removed) and the inlet temperature was maintained at 56°C. Total coating time was 30 minutes followed by an

-18-

additional 19 minute drying phase and 22 minutes of cooling at ambient temperature.

## EXAMPLE 4

5        A 10% by weight vinylidene chloride-based latex coated granular urea product was prepared in accordance with the procedures of Example 1 except that 400.0 grams of granular urea and 86.0 grams of Daran SL112 were used to make up the product; the latex was applied at a spray rate  
10      of 1.43 g./min. (0.00358 g. latex/g. fertilizer granule/min.). The fluidization/drying air flow rate was maintained between 122 and 128 m<sup>3</sup>/hr. (3.09-3.24 m<sup>3</sup>/g. water removed) with an inlet temperature of 46°C. Total coating time was 60 minutes followed by 18 minutes of  
15      drying at an inlet air temperature of 56°C and a 16 minute cooling phase at ambient temperature.

## EXAMPLE 5

20        A 10% vinylidene chloride-vinyl chloride latex coated granular urea product was prepared in accordance with the procedures of Example 1 except that 360.0 grams of granular urea and 71.6 grams of Geon 650X18 were used to make up the product; the latex was spray coated onto the fluidized urea at a rate of 1.26 g./min (0.00350 g.  
25      latex/g. fertilizer granule/min.). The fluidizing/drying air entered the fluid bed at 36-37°C and an air flow rate was maintained between 126 to 130 m<sup>3</sup>/hr. (3.70-3.82 m<sup>3</sup>/g. of water removed), and the air exited the bed at 32-34°C. Total coating time was 57 minutes which was  
30      followed by an 8 minute drying phase at an inlet air temperature of 36°C and 10 minutes of cooling using ambient air.

-19-

## EXAMPLE 6

A 10% vinylidene chloride-based latex coated granular urea product was prepared in accordance with the procedures of Example 1 except that 360.0 grams of granular urea and 72.7 grams of IXAN WA 50 were used to make up the product; the latex was applied to the urea through the bottom spray assembly at a rate of 1.01 g./min. (0.00281 g. latex/g. fertilizer granule/min.). The fluidization/drying air flow rate ranged from 123 to 128 m<sup>3</sup>/hr. (4.51-4.69 m<sup>3</sup>/g. water removed) and entered the bed at 44-52°C while exiting at temperatures of from 39-42°C. A 72 minute coating time was required to apply the 10% coating and was followed by a drying and a cooling phase.

## EXAMPLE 7

An attempt was made to produce a 10% vinylidene chloride-butylacrylate latex coated granular urea product as a latex coated product not within the scope of the present invention for purposes of conducting comparative testing. For this purpose, 360.0 grams of granular urea fertilizer were added into a fluidized bed Wurster column and an attempt was made to apply 83.3 grams of vinylidene chloride-butylacrylate latex (48-50% solids by weight, 5°C glass transition temperature) to the urea through the bed's bottom spray assembly. The latex was applied at an average rate of 0.83 g./min. (0.00231 g. latex/g. fertilizer granule/min.). The fluidization/drying air flow rate was maintained at 118 m<sup>3</sup>/hr. (4.65 m<sup>3</sup>/g. water removed) and at an inlet temperature of 33°C. Several minutes into the run, the partially coated urea granules began to agglomerate. As the run proceeded, the granules became more and more agglomerated. The coating was terminated after 36 minutes due to the agglomeration

-20-

which had caused the bed to become totally stagnant. A total of 29.8 grams of the latex (14.3 grams on a dry solids basis) was applied to the urea resulting in a 3.8% latex coating rather than the anticipated 10% coating weight which should have been achieved with the amount of urea and latex employed. Furthermore, the coating produced was very tacky and appeared to be uneven.

## EXAMPLE 8

A 9% by weight vinylidene chloride-based latex coated granular N-P-K fertilizer product was prepared in accordance with the procedure of Example 1 except that 450.0 grams of a granular N-P-K fertilizer with an analysis of 15-15-15 was placed into the fluid bed and 82.4 grams of Daran SL112 (44.5 grams on a dry solids basis) was applied to the fertilizer core at a rate of 3.05 g./min. (0.00678 g. latex/g. fertilizer granule/min.). The fluidization/drying air temperature was maintained at a temperature of 42-43°C at the air inlet, and at a rate of 120-123 m<sup>3</sup>/hr. (1.43-1.46 m<sup>3</sup>/g. water removed). The air exited the fluid bed at temperatures between 33 and 36°C. Following the completion of the latex coating process, the product was dried for 24 minutes at 42°C followed by 19 minutes of cooling with ambient air.

## EXAMPLE 9

A 9% vinylidene chloride-based latex coated prilled potassium nitrate product was prepared in accordance with the procedure of Example 1 except that 450.0 grams of prilled potassium nitrate was charged into the fluidized bed Wurster column and 82.4 grams of Daran SL112 was sprayed onto the fluidized potassium nitrate at a rate of 3.58 g./min. (0.00796 g. latex/g. fertilizer

-21-

granule/min.). The fluidization/drying air rate was maintained between 114 and 118 m<sup>3</sup>/hr. (1.15-1.19 m<sup>3</sup>/g. water removed). The air entered the bed at a temperature of 40-42°C and exited at 34°C. After coating was completed, 8 minutes of drying was performed at 41°C followed by 17 minutes of cooling with ambient air.

## EXAMPLE 10

A 10% vinylidene chloride-based coated granular potassium sulfate product was prepared in accordance with the procedure of Example 1 except that 500.0 grams of granular potassium sulfate (sulfate of potash) were charged into the bench-scale fluidized Wurster column and 89.9 grams of IXAN WA 50 (49.5 grams on a dry solids basis) were applied to the potassium sulfate at an average rate of 2.90 g./min. (0.00580 g. latex/g. fertilizer granule/min.). The fluidizing/drying air flow rate was maintained between 118 and 123 m<sup>3</sup>/hr. (1.51-1.57 m<sup>3</sup>/g. water removed). The air entered the fluid bed at a temperature of 42°C, and exited the bed between 32 and 36°C. After the coating was complete, the coated product was dried for an additional 15 minutes at an air temperature of 42°C followed by 12 minutes of cooling with ambient air.

## EXAMPLE 11

A series of dissolution rate tests was conducted on the coated fertilizer products of Examples 1-10 in order to measure the amount of nutrient released from the encapsulated fertilizers into water over varying periods of times. A sample of each of the coated products of Examples 1-10 was prepared and these sample products were immersed in water and the rate of dissolution of each of the products was determined after 1 hour, 1 day and 1 weeks of immersion.

-22-

Table 1 shows the results of the foregoing tests in terms of the cumulative nitrogen dissolution rate and, where applicable, the cumulative potassium dissolution rate (expressed in terms of  $K_2O$  dissolution rate) for each of the test samples. These test results provide an indication of the amount of nutrient released from a sample of encapsulated fertilizer into water over a specified period of time.

10

15

20

25

30



- 23 -

TABLE I

<u>Sample</u>	<u>Total Nitrogen Content</u>		<u>Cumulative Nitrogen Dissolution Rate (% Total N) (Observation Periods)</u>		<u>Total K<sub>2</sub>O Content</u>		<u>Cumulative K<sub>2</sub>O Dissolution Rate (% Total K<sub>2</sub>O) (Observation Periods)</u>	
	<u>1 Hr</u>	<u>1 Day</u>	<u>7 Day</u>		<u>1 Hr</u>	<u>1 Day</u>	<u>7 Day</u>	
Example 1	39.1	3.1	6.0	9.7	--	--	--	--
Example 2	43.6	7.9	24.1	56.2	--	--	--	--
Example 3	42.2	2.0	6.3	14.5	--	--	--	--
Example 4	41.4	5.1	7.5	13.2	--	--	--	--
Example 5	41.6	4.2	15.3	26.1	--	--	--	--
Example 6	41.5	2.9	6.5	13.0	--	--	--	--
Example 7	44.7	66.2	98.2	*	--	--	--	--
(Control)								
Example 8	13.7	5.8	13.6	18.8	13.7	0.6	2.7	5.7
Example 9	13.6	9.0	15.5	28.9	42.7	7.7	13.1	19.8
Example 10	--	--	--	--	47.4	2.0	13.0	30.4

\* Testing was terminated for this sample after 1 day in view of the nearly 100% cumulative dissolution at that point.

-24-

From these tabulated results, it can be seen that the encapsulated fertilizers of the present invention demonstrate relatively low dissolution rates indicating no significant defects in the coatings which would result in rapid nutrient release. However, it can be seen that the results achieved with the product of Example 2 are indicative that coating weights at such level and lower normally are to be avoided. Furthermore, the low one week dissolution rates of the remaining samples demonstrate the effectiveness of the latex encapsulated fertilizers of the present invention to function as controlled release nutrient sources with extended fertilizer residuals. These extended residual characteristics enable the present products to be used as nursery application fertilizers.

## EXAMPLE 12

A series of nutrient leaching tests was conducted in order to determine the temperature sensitivity of the release rate of the latex encapsulated fertilizers of the present invention. In this regard, the temperature sensitivity of an encapsulated fertilizer is important in determining its overall value as a controlled, slow release fertilizer. If the coating is highly temperature sensitive, it will have a release rate that varies along with the temperature at which it is used. This can create problems for fertilizers that are used in differing climates. For example, an encapsulated fertilizer with a temperature sensitive release rate might be an effective 8-9 month nursery-type product in cooler climates, such as the northern United States, but in warmer climates, like those in the southern U.S., this same product may only be effective for 4-5 months. Many of the current polymer encapsulated fertilizers are fairly temperature sensitive, and thus have higher release rates and less residual in

-25-

warmer climates, where a majority of nursery-type fertilizers are used.

The tests were run on two sample encapsulated fertilizer products one of which was the product from Example 3 and the other was the product of Example 4. For comparative purposes, commercially available solvent applied polymer encapsulated fertilizers sold under the respective trademarks "Nutricote" 270 Day by Chiso-Asahi Fertilizer Company (a polyethylene coated ammonium nitrate and potassium sulfate product) and "Osmocote" 37-0-0 by Sierra Chemical Company (a dicyclopentadiene and vegetable oil copolymer encapsulated urea product) were tested. Additionally, a sulfur coated urea product (identified as "S-907" herein) was also included in the testing as a further comparative sample. The sample S-907 product was prepared by applying a 25% sulfur coating on a granular urea in a coating drum.

The testing consisted of collecting the nitrogen leached out of each of the sample encapsulated fertilizer products at both 70°F and 100°F at two week intervals. The results of these tests are set forth in Table II.

TABLE II

Sample	17 Days		31 Days		46 Days	
	70°F	100°F	70°F	100°F	70°F	100°F
Example 3	52	105	36	103	65	98
Example 4	20	70	22	42	16	19
Nutricote 270 Day	170	378	132	270	195	283
Osmocote 37-0-0	35	140	87	155	280	132
S-907 Sulfur Coated Urea	238	330	140	197	128	215
Control	7	16	7	8	5	5
Least Signif. Diff. (5%)	101	101	93	93	67.5	67.5

-26-

It is evident from Table II that the nitrogen content of the leachate was consistently less for the vinylidene chloride-based latex encapsulated fertilizer samples of the present invention (Examples 3 and 4) than it was for  
5 Nutricote, Osmocote or sulfur coated urea (S-907). In addition, the temperature sensitivity of the latex coated samples of the present invention was minimal, as evidenced by the increases in nitrogen leachate at 100°F being less than the least significant difference. Accordingly, the  
10 results of this study indicate that the latex encapsulated fertilizers of this invention have low release rates and that these release rates are not influenced significantly by temperature differences.

15

## EXAMPLE 13

A greenhouse study was conducted to determine the agronomic benefits of the encapsulated fertilizers of this invention, and to compare the agronomic performance of these new fertilizers with current nursery-type industry  
20 standards. Samples of encapsulated fertilizers were applied at a rate of 2 pounds of nitrogen per 1000 square feet to Coventry Kentucky bluegrass growing in small (4 inch diameter) pots. The fresh weight of the grass clippings was found for each of these pots at various time  
25 intervals. By monitoring the fresh weight of the clippings, and comparing the results with control pots (those without any fertilizer) and pots treated with a commercially available encapsulated fertilizer ("Nutricote" 270 Day) as well as with a sulfur coated urea  
30 product (S-907) and a pot treated with granular urea, the agronomic benefits of the present latex encapsulated fertilizers were determined.

-27-

Table III contains fresh weight data at the various time intervals.

TABLE III

5 Cumulative Fresh Weight (in grams) at Number Days

Sample	25	39	52	67	81	95	112
Example 3	0.55	0.90	1.38	1.85	2.25	2.58	2.85
Nutricote 270 Day	0.50	0.65	0.88	1.08	1.30	1.58	1.83
10 S-907 Sulfur Coated Urea	0.72	1.50	2.57	3.39	3.92	4.24	4.50
Granular Urea	2.43	3.45	4.17	4.83	5.30	5.73	6.10
Control	0.36	0.43	0.50	0.70	0.80	0.87	0.95

15 Virtually any fertilizer or plant nutrient may be used in the practice of the invention including by way of example, urea, urea-formaldehyde composites, ammonium nitrate, ammonium sulfate, potassium chloride, potassium nitrate, potassium sulfate and monoammonium phosphate. In  
20 addition, a combination of active ingredients may be used, as for example, more than one fertilizer or a fertilizer and a pesticide or other non-fertilizer ingredient.

The foregoing is a description of illustrative  
25 embodiments of the invention, and it is applicants' intention in the appended claims to cover all forms which fall within the scope of the invention.

30

-28-

We claim:

1. A coated product comprising a water soluble core material having a water insoluble polymeric coating  
5 encapsulating said core, said encapsulating coating comprising a water-borne, polyvinylidene chloride-based latex composition which provides for the release of said water soluble core material over an extended period of time.
- 10 2. The coated product of claim 1 wherein said core material is in particulate form.
- 15 3. The coated product of claim 1 wherein said core material is selected from the group consisting of fertilizers, pesticides, herbicides, fungicides, growth regulators, insecticides, animal and insect repellents and mixtures thereof.
- 20 4. The coated product of claim 2 wherein said latex composition is spray coated on said core material and has a water-like viscosity enabling low pressure spraying thereof onto said core material without causing shear related breakdown of said latex composition.
- 25 5. The coated product of claim 4 wherein said latex composition has a solids content, a glass transition temperature and a blocking temperature sufficient to enable said spray coating of said latex composition on  
30 said core material without causing said particles to agglomerate.

-29-

6. The coated product of claim 4 wherein the viscosity of said latex composition is less than about 30 centipoise.

5 7. The coated product of claim 5 wherein said latex composition has a solid content of greater than about 50 percent by weight (on a solid basis).

10 8. The coated product of claim 7 wherein said latex composition has a glass transition temperature in the range of about 15-35°C.

15 9. The coated product of claim 5 wherein said latex composition has a glass transition temperature ranging from a lower limit of about 30°C below the temperature at which the spray coating is performed to an upper limit approaching but not exceeding said spray coating temperature.

20 10. The coated product of claim 9 wherein said spray coating temperature is in the range of about 35-60°C.

25 11. The coated product of claim 8 wherein said latex composition has a blocking temperature of at least about 32°C.

30 12. The coated product of claim 1 wherein said latex composition is selected from the group consisting of copolymer blends of predominately vinylidene chloride monomers and ethylenically unsaturated comonomers selected from the group consisting of methyl methacrylates, acrylonitriles and methyl acrylates, vinylidene chloride-vinyl chloride copolymers and mixtures thereof.

-30-

13. The coated product of claim 12 wherein said copolymer blends of vinylidene chloride monomers and ethylenically unsaturated comonomers contain about 80-92% by weight of said vinylidene chloride monomers and about  
5 5-14% by weight of said ethylenically unsaturated comonomers.

14. The coated product of claim 13 wherein said latex composition contains about 0.05-0.5% by weight of an  
10 anionic surfactant and about 3-5% by weight of a nonionic surfactant.

15. The coated product of claim 14 wherein said anionic surfactant is selected from the group consisting  
15 of sodium alkylbenzensulfonate, sodium salts of alkyl sulfonic acid esters, sodium salts of sulfosuccinic acid alkyl esters, sodium alkylsulfonates, sodium alkylidiphenylether sulfonates, sulfuric acid esters of alkylophenolpolyethylene oxides and mixtures thereof.

20 16. The coated product of claim 14 wherein said nonionic surfactant is selected from the group consisting of alkylethers, alkylphenol ethers, fatty acid esters of polyethylene oxides and mixtures thereof.

25 17. The coated product of claim 12 wherein the latex composition encapsulating said core is coated thereon at a coating weight of from about 4% to about 20% by weight.

30 18. The coated product of claim 12 wherein said latex composition has a maximum moisture vapor transmission rate for an 0.1 mil film of about 2.0 grams per 100 square inches per 24 hours at 100°F and 90% relative humidity.



-31-

19. A controlled-release fertilizer product comprising a core containing a water soluble fertilizer in particulate form encapsulated within a coating, said coating comprising a water-borne, polyvinylidene chloride-based latex composition.

20. The controlled-release fertilizer product of claim 19 wherein said latex composition is spray coated on said core particles and has a viscosity of less than about 30 centipoise, a solids content of greater than about 50 percent by weight (on a solids basis), a glass transition temperature in the range of about 15-35°C and a blocking temperature of at least about 32°C.

21. The controlled-release fertilizer product of claim 20 wherein said glass transition temperature is in a range from a lower limit of about 30°C below the temperature at which said spray coating is performed to an upper limit approaching but not exceeding said spray coating temperature.

22. The controlled-release fertilizer product of claim 21 wherein said spray coating temperature is in the range of about 35-60°C.

23. The controlled-release fertilizer product of claim 19 wherein said latex composition is selected from the group consisting of copolymer blends of predominately vinylidene chloride monomers and ethylenically unsaturated comonomers selected from the group consisting of methyl methacrylates, acrylonitriles and methyl acrylates, vinylidene chloride-vinyl chloride copolymers and mixtures thereof.

-32-

24. The controlled-release fertilizer product of claim 23 wherein said copolymer blends of vinylidene chloride monomers and ethylenically unsaturated comonomers contain about 80-92% by weight of said vinylidene chloride monomers and about 5-14% by weight of said ethylenically unsaturated comonomers.

25. The controlled-release fertilizer product of claim 24 wherein said latex composition contains about 0.05-0.5% by weight of an anionic surfactant and about 3-5% by weight of a nonionic surfactant.

26. The controlled-release fertilizer product of claim 25 wherein said anionic surfactant is selected from the group consisting of sodium alkylbenzenesulfonate, sodium salts of alkyl sulfonic acid esters, sodium salts of sulfosuccinic acid alkyl esters, sodium alkylsulfonates, sodium alkylidiphenylether sulfonates, sulfuric acid esters of alkylophenolpolyethylene oxides and mixtures thereof.

27. The controlled-release fertilizer product of claim 25 wherein said nonionic surfactant is selected from the group consisting of alkylethers, alkylphenol ethers, fatty acid esters of polyethylene oxides and mixtures thereof.

28. The controlled-release fertilizer product of claim 23 wherein the latex composition encapsulating said core is coated thereon at a coating weight of from about 4% to about 20% by weight.

-33-

29. The controlled-release fertilizer product of claim 23 wherein said latex composition has a maximum moisture vapor transmission rate for an 0.1 mil film of about 2.0 grams per 100 square inches per 24 hours at 100°F and 90% relative humidity.

30. A process for the preparation of a controlled release product comprising coating a water soluble core composition in particulate form with a water insoluble polymeric coating comprising a water-borne, polyvinylidene chloride-based latex composition.

31. The process of claim 30 wherein said latex composition is coated on said particulate core composition by spray coating said latex composition thereon in a manner such that said particles are encapsulated in said latex coating.

32. The process of claim 31 wherein said latex composition is spray coated on said core composition in a fluidized bed and said particles encapsulated in said latex coating are hot air dried.

33. The process of claim 32 wherein said latex composition has a water-like viscosity and is low pressure spray coated on said core composition in a manner such that shear related breakdown of said latex composition is avoided.

34. The process of claim 32 wherein said latex composition is coated on said core composition in a manner such that agglomeration of said particles is avoided, said latex composition having a solids content, a glass transition temperature and a blocking temperature

-34-

sufficient to promote said spray coating without causing agglomeration.

5        35. The process of claim 34 wherein said latex composition has a viscosity of less than about 30 centipoise, a solids content of greater than about 50 percent by weight (on a solids basis), a glass transition temperature in the range of about 15-35°C and a blocking temperature of at least about 32°C.

10       36. The process of claim 32 wherein said latex composition is spray coated on said core composition at a temperature in the range of about 35-60°C.

15       37. The process of claim 36 wherein said latex composition has a glass transition temperature in a range of from about 30°C below said spray coating temperature up to a temperature approaching but not exceeding said spray coating temperature.

20       38. The process of claim 30 wherein said latex composition is selected from the group consisting of copolymer blends of predominately vinylidene chloride monomers and ethylenically unsaturated comonomers selected  
25       from the group consisting of methyl methacrylate, acrylonitriles and methyl acrylates, vinylidene chloride-vinyl chloride copolymers and mixtures thereof.

30       39. The process of claim 38 wherein said copolymer blends of vinylidene chloride monomers and ethylenically unsaturated comonomers contain about 80-92% by weight of said vinylidene chloride monomers and about 5-14% by weight of said ethylenically unsaturated comonomers.

-35-

40. The process of claim 39 wherein said latex composition contains about 0.05-0.5% by weight of an anionic surfactant and about 3-5% by weight of a nonionic surfactant.

5

41. The process of claim 40 wherein said anionic surfactant is selected from the group consisting of sodium alkylbenzenesulfonate, sodium salts of alkyl sulfonic acid esters, sodium salts of sulfosuccinic acid alkyl esters, sodium alkylsulfonates, sodium alkylidiphenylether sulfonates, sulfuric acid esters of alkylphenol-polyethylene oxides and mixtures thereof.

42. The process of claim 40 wherein said nonionic surfactant is selected from the group consisting of alkylethers, alkylphenol ethers, fatty acid esters of polyethylene oxides and mixtures thereof.

43. The process of claim 30 wherein said latex composition is coated on said particulate core at a coating weight of from about 4% to about 20% by weight.

44. The process of claim 31 wherein said spray coating is performed at an application rate of about .0025 grams latex per gram of fertilizer granule per minute to about .0083 grams latex per gram of fertilizer granule per minute.

45. The process of claim 44 employing a fluidizing air flow rate in the range of about 1-6 cubic meters per hour per gram of water to be removed from said coating.

46. The process of claim 45 wherein said spray coating is conducted at a temperature in the range of about 35-60°C.

# INTERNATIONAL SEARCH REPORT

International Application No. PCT/US91/01950

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (if several classification symbols apply, indicate all) <sup>6</sup>		
According to International Patent Classification (IPC) or to both National Classification and IPC		
US Cl. 71/119, 3 <sup>+</sup> ; 427/212		
IPC C05C 9/00; C05G 5/00; B01J 8/24; B05D 7/00		
<b>II. FIELDS SEARCHED</b>		
Minimum Documentation Searched <sup>7</sup>		
Classification System	Classification Symbols	
US.Cl.	71/119, 32, 33, 48, 49, 64.02, 64.11, 64.13 427, 212, 213 ; 106/18.31, 18.32, 18.33, 15.05, 285, 287.3	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched <sup>8</sup>		
Prior art cited in specification		
<b>III DOCUMENTS CONSIDERED TO BE RELEVANT <sup>9</sup></b>		
Category <sup>*</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>
<u>Y</u> A	US, A, 4,759,956 (AMER ET AL.) 26 July 1988, col. 4, lines 15-16, claim 1.	30-46 1-29
<u>Y</u> A	US, A, 3,992,558 (SMITH-JOHANNSEN ET AL.) 16 November 1976, col. 7, line 14, Abstract	30-46 1-29
Y	US, A, 4,401,788 (HIYOSHI ET AL.) 30 August 1983, Col. 2, lines 47-68	1-29
Y	US, A, 4,198,782 (KYDONIEUS ET AL.) 22 April 1980, whole document	1-29
Y	JA 0042923, (CHISSO CORP) 18 December 1971, Abstract	1-29
<p><sup>*</sup> Special categories of cited documents: <sup>10</sup></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&amp;" document member of the same patent family</p>		
<b>IV. CERTIFICATION</b>		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
4 June 1991	05 JUL 1991	
International Searching Authority	Signature of Authorized Person	
ISA/US	Brian G. Bemberick <i>Brian G. Bemberick</i>	

## FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

V. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE<sup>1</sup>

This international search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers \_\_\_\_\_ because they relate to subject matter<sup>12</sup> not required to be searched by this Authority, namely:

2. ☐ Claim numbers \_\_\_\_\_, because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out<sup>13</sup>, specifically:

3. ☐ Claim numbers \_\_\_\_\_, because they are dependent claims not drafted in accordance with the second and third sentences of PCT Rule 6.4(a).

VI. ☒ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING<sup>2</sup>

This International Searching Authority found multiple inventions in this International application as follows:

- I. Coated Fertilizer products and a method of preparing class 71/3<sup>+</sup>, claims 1-46;
- II. Coated herbicide products and a method of preparing class 71/65<sup>+</sup>, claims 1-18 and 30-43; (cont.)

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.

2. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:

3. ☒ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:

1-46 as they read on a coated fertilizer product and method of preparing.

4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

- ☐ The additional search fees were accompanied by applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

PCT/US91/01950

Continuation Sheet

- III. Coated Fertilizer/Pesticide compositions and a method of preparing, class 71/3+ claims 1-18 and 30-43;
- IV. Coated fungicide products and a method of preparing, class 514/12+, claims 1-18 and 30-43;
- V. Coated insecticide products and a method of preparing, class 514/12+, claims 1-18 and 30-43;